

General Information

Description

SEETEC VA800 resin is produced by ExxonMobil Chemical's autoclave process technology. SEETEC VA800 resin, with 28% VA content, is an excellent raw material in the application of hot melt adhesives.

Additives

- ◆ Antioxidant
- ◆ Free flow agent

Applications

- ◆ Hot melt adhesives

Physical Properties¹

Properties	Nominal Value	Unit	Test Method
Melt Index	20.0	g/10min	ASTM D1238
Vinyl Acetate	28	wt. %	LC Method
Density	0.950	g/cm ³	ASTM D1505
Melting Point	69	°C	LC Method
Hardness	25	D scale	ASTM D2240
Vicat Softening Point	< 40	°C	ASTM D1525

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications